


Printing Tips



GMUND BLANC BEIGE

Screens

- o In offset printing 54 - 60 l/cm, in some cases up to 80 l/cm

Recommendations for offset printing

- o Match litho to the paper colour
- o Under colour reduction and low printing stacks when applying strong ink coverage
- o Proof printing on same paper stock
- o Use of fully oxidative drying inks
- o Very low ink absorption due to the calendered paper surface. Careful drying, minimum of 24 hours required

Further applications

- o 90 g/m² suitable for laser and inkjet printing in desktop applications
- o Letterpress, blind embossing, hot foil stamping, paper etching, thermography, silk-screen printing, die cutting

Finishing and processing

- o Very interesting results with blind embossing, die cutting and hot foil stamping
- o Well suitable for bookbinding and packaging

Special advice

- o Attractive results in offset printing on the calendered surface
- o Chlorine and acid free, pH neutral and therefore very age-resistant

For all printing and processing techniques, the recommendations of the manufacturers of machines, inks, glues, lamination and embossing foils etc. have to be followed. For any damages caused by improper application of Gmund paper in regards of printing and processing, Gmund cannot accept liability.