

Printing Tips

lakepaper EMOTION

Screens

- In offset printing 54 – 60 l/cm, in some cases up to 80 l/cm

Recommendations for offset printing

- For coloured papers match litho to the paper colour
- Under colour reduction and low printing stacks when applying strong ink coverage
- Proof printing on same paper stock
- Use of fully oxidative drying inks
- Careful drying, a minimum of 24 hours

Further applications

- EMOTION in 90 and 120 g/m² is suitable for laser and inkjet printing in desktop applications, assumed that the individual technical settings for the printer are taken into consideration
- Letterpress, blind embossing, hot foil stamping, paper etching, thermography, silk-screen printing, die cutting, steel engraving

Finishing and processing

- Very interesting results with blind embossing, die cutting and hot foil stamping
- Well suitable for bookbinding and packaging

Special advice

- Attractive results in offset printing on the structured surface
- Chlorine and acid free, pH neutral and therefore very age-resistant

For all printing and processing techniques, the recommendations of the manufacturers of machines, inks, glues, lamination and embossing foils etc. have to be followed. For any damages caused by improper application of lakepaper papers in regards of printing and processing, lakepaper cannot accept liability.