

## Printing Tips

**extra** 

### lakepaper EXTRA+

#### Screens

- In offset printing 54 – 60 l/cm, in some cases up to 80 l/cm

#### Recommendations for offset printing

- Match litho to the paper
- Under colour reduction and low printing stacks when applying strong ink coverage
- Proof printing on same paper stock
- Use of fully oxidative drying inks
- Low ink absorption due to the embossed respectively calendered paper surface. Careful drying, a minimum of 24 hours

#### Further applications

- 90, 100 and 115 g/m<sup>2</sup> suitable for laser and inkjet printing in desktop applications, assumed that the individual technical settings for the printer are taken into consideration
- Letterpress, blind embossing, hot foil stamping, paper etching, thermography, silk-screen printing, die cutting, steel engraving

#### Finishing and processing

- Very interesting results with blind embossing, die cutting and hot foil stamping
- Well suitable for bookbinding and packaging

#### Special advice

- Attractive print results on all surfaces
- Chlorine and acid free, pH neutral and therefore very age-resistant

For all printing and processing techniques, the recommendations of the manufacturers of machines, inks, glues, lamination and embossing foils etc. have to be followed. For any damages caused by improper application of lakepaper papers in regards of printing and processing, lakepaper cannot accept liability.